

# Product datasheet ISOFOLAN®

## 1 Identification of the substance / preparation / company

### Product details

Trade name:	ISOFOLAN®
Application of the substance / preparation:	Manufacture of dental pressure moulding splints (placeholder slide)
Manufacturer / Supplier:	Scheu Dental GmbH Am Burgberg 20 58642 Iserlohn Germany Tel. 0049 2374 9288-0

## 2 Composition / information on ingredients

### Chemical characterization

CAS-Number:	9002-88-4
Designation:	Polyethylen high density (PE-HD)

## 3 Handling and storage

### Handling

Information for safe handling:	When using do not eat, drink or smoke. Provide suction extractors if dust is formed.
--------------------------------	---

### Storage

Storage conditions:	Store dry and dark at max. 30°C.
---------------------	----------------------------------

## 4 Physical, chemical, mechanical and biological properties

### 4.1 General properties

Properties	Guideline	Value
Form	-	Solid
Colour	-	Milky-white
Odour	-	Odourless
Density	ISO 1183	0,919 g/cm <sup>3</sup>
Water absorption after 24 h at 23°C	ISO 62 Methode 1	<0,1 %

## Product datasheet ISOFOLAN®

### 4.2 Mechanical properties

Properties	Guideline	Value
Tensile strength	ISO 527	30 MPa
Flexional strength	ISO 527	-
Impact strength 23°C	ISO 5256	no fracture
Notched 23°C	ISO 179	no fracture
Yield strain	ISO 527	20 %
Yield stress	ISO 527	9 MPa
Elongation at tear	ISO 527	>400 %
E-modulus	ISO 527	<600 MPa
Hardness Shore A	DIN 53505	-
Hardness Shore D	DIN 53505	45
Rockwell Hardness	ISO 2039-1 H49/30	15

### 4.3 Thermal properties

Vicat softening point	ISO 306 Methode A 50	93 °C
	ISO 306 Methode B 50	45 °C
Thermoform resistance	ISO 75 Methode B	41 °C
Continuous stress temperature	ISO 75	60-75 °C

### 4.4 Biological properties / Biocompatibility

The material has been tested on biocompatibility according to DIN EN ISO 10993. It meets the requirements regarding biological compatibility for medical products / devices.

### 5 Stability and reactivity

#### Thermal decomposition / Conditions to avoid:

No decomposition by intended use

### 6 Disposal

The material can be recycled after separation of disposed of like commercial or household waste.

The aforementioned data are given most conscientiously but without any obligation. Any processing details are provided merely for guidance: it is the user's responsibility to check the suitability of the product for the intended application.